




Unit 6, 8th Floor, Kiyān Tower,
No. 2551, Vali Asr Street,
Tehran 1968643152, Iran
Tel: +98 21 88645242
Fax: +98 21 88645241

ISB
ترکیب‌های بن‌سینا

TECHNICAL DATA SHEET

Product Name: Maleic Anhydride



CAS NO.: 108-31-6

Prepared: Oct 2023

No.	Item	Unit	Value	Test Method
1	Color	Hazen	Max. 30	ASTM D1209
2	Iron	ppm wt	Max. 2.0	ASTM D1068
3	Purity	wt %	Min. 99.5	ASTM D2930
4	Ash	ppm wt	Max. 20	ASTM D482
5	MAc Content	wt %	Less than 0.3	ASTM D2930
6	Solidification point	°C	Min. 52.3	ASTM D1493
7	Color Stability	Hazen	Max. 80	ASTM D3366
8	Appearance	-	Colorless Liquid	-

Transportation: In tanker truck / isotank (T11)



Note: Product must be heated to min. 65°C, but not more than 75°C for unloading. Heating medium such as steam or hot water may be required for unloading.